

FICHE TECHNIQUE

REFERENCE : SBR 1001/BLC/2PLIS/S

PROPRIETES	VALEURS
MATIERE	SBR
COLORIS	Blanc
PRESENTATION	2 faces lisses - 2 plis
DENSITE	1.65
DURETE	55 ± 5 sh A
RESISTANCE A LA TRACTION	45 Kg/cm ²
ALLONGEMENT RUPTURE	400%
COMPRESSION (22 heures à 70°C)	NA
TENUE A LA TEMPERATURE	De -15°C à +70°C